



21. (Thrice Amended) A method of manufacturing a liquid toner composition for electrophotography, comprising:

heating a thermoplastic resin within a solvent capable of dissolving said thermoplastic resin when heated and substantially incapable of dissolving said resin at room temperature, an SP (solubility parameter) value of said solvent being adjusted to control the particle diameter of toner particles on a basis of a difference between an SP value of the resin and the SP value of the solvent, while stirring the thermoplastic resin in said solvent together with inorganic particles and a coloring agent subjected to dispersion and mixing, to thereby dissolve said thermoplastic resin in said solvent; and

cooling the mixture to permit precipitation of the toner particles.

22. (Twice Amended) A method of manufacturing a liquid toner composition for electrophotography, according to claim 21, wherein said liquid toner composition includes one or more antistats selected from the group consisting of nigrosine series dyes, metal soaps, alkylbenzene sulphonates, phospholipids and organic amines.

24. (Amended) The method of manufacturing a liquid toner composition for electrophotography according to claim 22, wherein said liquid toner composition includes a dispersant, and said dispersant is added in an amount of 0.5 to 80% by weight based on the solid components of the liquid toner composition.

28. (New) A method of manufacturing a liquid toner composition for electrophotography, according to claim 22, wherein

53 said metal soaps are selected from the group consisting of manganese naphthenate, calcium naphthenate, zirconium naphthenate, cobalt naphthenate, iron naphthenate, lead naphthenate, nickel naphthenate, chromium naphthenate, zinc naphthenate, magnesium naphthenate, manganese octylate, calcium octylate, zirconium octylate, iron octylate, lead octylate, cobalt octylate, chromium octylate, zinc octylate, magnesium octylate, manganese dodecylate, calcium dodecylate, zirconium dodecylate, iron dodecylate, lead dodecylate, cobalt dodecylate, nickel dodecylate, chromium dodecylate, zinc dodecylate and magnesium dodecylate;

said alkylbenzene sulphonate are selected from the group consisting of calcium dodecylbenzene sulphonate, sodium dodecylbenzene sulphonate, and barium dodecylbenzene sulphonate;

said phospholipids are selected from the group consisting of lecithin and cephalin; and

said organic amines are n-decylamine.